

MANDARIN STONE

PRODUCT SPECIFICATION Classic Calacatta Tumbled Stone

Technical features - compliant with standards EN 14411 (ISO 13006) annex G group Bia GL

Technical Features	Reference	Average Value
Reaction to Fire	96/603/EC	NPD
Flexural Strength – Mean Value	EN 12372	10,1
Abrasion Resistance	EN 14157	13,16
Water absorption at atmospheric pressure (by mass)	EN 13755	0,1
Water absorption at atmospheric pressure (by volume)		0,1
Apparent Density	EN1936	2715
Slip Resistance Value – Wet	EN 14231	33
Slip Resistance Value – Dry		53
Open Porosity	EN 1936	0,22
Flexural strength after freezing	EN 14066	After freezing = 8,70